



# PINE PLYWOOD

ITEM	PINE PLYWOOD	
GLUE	E0, E1, E2 , P2	
CORE	Mix Acacia and Eucalipto (Hardwood)	
THICKNESS AND TOLERANCE	3mm-32mm or upon request (+-0.3mm, +0.5mm) Core pine , poplar	
SPECS	No Sanded/ Sanded both side	
FACE/BACK	Natural Pine Veneer	
HOT PRESS TIME	A & B type -2 times for core and 1 time for film	
MOISTURE CONTENT	8%-12% at the time of shipment	
USAGE	Real estate construction / formwork panel / furniture /cabinets/ closet	
PACKAGE	Outer packing: pallets are covered with plywood or carton boxes and strong steel belts	
CERTIFICATION	FSC, CARB P2, APHIS, USDA	
DRY TEST CONDITION	± 3 % factory moisture content	
WET/DRY TEST CONDITION	± 3 % of original moisture content	
REGULATION PS 1-09:	YES	
TYPE OF EXHIBITION	Exposure 1)	
PERFORMANCE CATEGORY AND THICKNESS TOLERANCE	0,5 mm	
APPLIED PRESSURE	69 kPa (10 psi)	
GRADE	BB/ BC / CC / CD / DD	

